

Test Report No. SDHG1404004839FB Date: Apr.18, 2014 Page 1 of 2

Pro Light Concepts Ltd
Perseverance Mill, Olive Lane, Darwen, Lancashire BB3 3DQ (UK)

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description : HEAVY DUTY FABRIC

Sample Receiving Date : Apr.14, 2014

Test Performing Date : Apr.14, 2014 to Apr.18, 2014

Test Result Summary

| No. | Test(s) Requested | Result(s) | Comments | | | |
|--|--|-----------|----------|--|--|--|
| 1 | California Technical Bulletin 117-2013 Section 1 | PASS | / | | | |
| For further details, please refer to the following page(s) | | | | | | |

Signed for and on behalf of SGS-CSTC Co., Ltd.

Irvette Zhang
Approved signatory

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and

15.1 BuildingEuropean Industria Part Vis.1 Sturtherum Road Waste Section Dalary Town Sharek, Forters, Guargetong Drina 528333 t (86—757)22805888 f (86—757)22805858 www.sgsgroup.com.cn 中国・广东・保山市政策区大良街道办事处五沙版和素路1号欧州工业园一号厂房首层 報稿: 528333 t (86—757)22805888 f (86—757)22805858 e sgs. china@sgs.com



No. SDHG1404004839FB Date: Apr.18, 2014 Page 2 of 2 **Test Report**

Test Conducted:

TB117 Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture-2013 Section 1- Cover Fabric Test

I. Sample Details

| Material: Fabric / Color Black | Code: STAR21 / 20 / 30 / 22 / 19 / 11 / 12 / 13 | Density of sample: | 416 g/m ² |
|--------------------------------|---|--------------------|----------------------|
|--------------------------------|---|--------------------|----------------------|

II. Test Condition

| | Temperature | Relative humidity | Duration |
|---|-------------|-------------------|----------|
| Conditioning of test samples and cigarettes | (21±3) °C | RH < 55 % | 24h |

III. Acceptance Criteria:

- 1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
- a) The mock-up test specimen continues to smolder after the 45 minutes test duration;
- b) A vertical char length of more than 1.8 inches develops on the cover fabric;
- The mock-up test specimen transitions to open flaming.
- The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.
- 3. If more than one initial specimen fails, the cover fabric fails the test.
- 4. If any one of the three initial specimens fails, repeat the test on additional three specimens.5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

Photo Appendix:

IV. Test Result

| Specimen # | Duration of smouldering (min : sec.) | Open flaming (YES/NO) | Vertical Char Length (inches) | Rating |
|------------|---------------------------------------|--------------------------|-------------------------------|--------|
| 1 | 30min20s | NO | 0.7 | PASS |
| 2 | 29min48s | NO | 0.6 | PASS |
| 3 | 30min16s | NO | 0.7 | PASS |

Conclusion: PASS



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-an

1F, "BuildingEuropein Industrial Park, No.1 Sturterian Road, Wurfe Section, Dallang Town, Sturde, Forters, Guargitong China 528333 t (86-757)22805888 f (86-757)22805888 www.sgs.group.com.cn 中国·广东·傳山市殿議区大良街道办事处五沙版和素」1号欧洲工业园一号厂房首层 維備: 528333 t (86-757)22805888 t (86-757)22805858 e sgs.china@sgs.com

^{***}End of Report***